SUNDWIGER Messingwerk

Bronze (Copper-Tin) **BB21**



Material Designation			
DIN-EN Symbol	CuSn2Zn2Fe		
DIN-EN	-		
UNS	C50725		
JIS	-		
The Miller Company	C50725		

Physical Properties*			
Electrical conductivity soft	19	MS/m	
Thermal conductivity	150	W/(m·K)	
Thermal expansion coefficient **	17.5	10-6/K	
Density	8.9	g/cm³	
Modulus of elasticity	120	GPa = kN/mm²	

- * Reference values at room temperature
- ** Between 20 and 300 °C

Nominal Composition (mass content in %)		
Cu	Balance	
Sn	2	
Zn	2.2	
Ni	< 0.2	
Fe	0.1	
Pb	< 0.005	
P	0.028 - 0.04	
Other	< 0.1	

Typical Applications

- Connectors for electrical engineering, electronics and automotive technology
- · Stamped-bent parts
- Contact springs
- Leaf springs for relays

About The Alloy

BB21 is a 2% phosphor bronze with additions of 2.2% Zn and 0.1% Fe which exhibits a good combination of strength, electrical conductivity and metal value. It is used for connectors and current-carrying springs in contacts.

Tin bronze with about 2% Sn exhibit a higher electrical conductivity compared to the standard bronzes. Due to coherent precipitates BB21 has improved strength. Although the tin content is reduced, mechanical properties are similar to CuSn4. By means of an additional tempering after the cold forming process the bendability can be further improved.

The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.

Mechanical Properties *)						
Temper condition		O R 290 H 70	H02 R 390 H 120	H03 R 480 H 150	H04 R 540 H 170	H06 R 610 H 190
Tensile strength in N/mm²		290 - 390	390 - 500	480 - 555	510 - 600	600 - 665
0.2 % yield strength in N/mm²		< 190	280	430	470	575
Elongation A _{L50} %		> 40	> 20	> 10	> 6	> 3
Vickers hardness HV		70 - 100	120 - 160	150 - 185	170 - 200	190 - 220
Electrical conductivity in % IACS		32	31	31	31	31
Minimum radius of the bending mandrel for 90° bend and strip thickness s, tempered quality						
0.10 ≤ s ≤ 0.25 mm	transverse parallel	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	0 x s 1 x s	0 x s 1.5 x s
0.25 < s ≤ 0.5 mm	transverse parallel	0 x s 0 x s	0 x s 0 x s	0 x s 1 x s	0.5 x s 1 x s	1 x s 2 x s
*) Reference values						

SUNDWIGER Messingwerk





Processing Instructions		
Cold forming properties	very good	
Machinability	sufficient	
Electroplating properties	very good	
Hot-dip tinning properties	very good	
Soldering	very good	
Resistance welding	good	
Gas shielded arc welding	good	
Laser welding	very good	

Available Dimensions

Bright pre-rolled strip 1 to 2.5 mm

Precision strip thickness from 0.05 to 1.2 mm

Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness

Other widths available on request.

Available Versions

Coils with standard outer diameters of 1200 mm

Strip in reel form with coil weight of up to 1500 kg

Multipancake up to 2.5 t

Hot-dip tinned strip

Profiled strip

Electroplated strip (tin, nickel)

Your Local Contact Person

USA Europe Asia

SUNDWIGER

Messingwerk

Sundwiger Messingwerk GmbH

Hönnetalstraße 110 58675 Hemer Germany Phone +49 2372 661-0 Fax +49 2372 661-259 E-Mail: sales-sundwig@sundwiger-

www.sundwiger-mw.com

The Miller Company

275 Pratt Street CT 06450 Meriden Phone +1 203 63969-02 Fax +1 203 63969-24 E-Mail: sales@themillerco.com

www.sundwiger-mw.com

SUNDWIGER

Messingwerk

Diehl Metall (Shenzhen) Co. Ltd.

Block 25

Shatoujiao Free Trade Zone 518081 Shenzhen - P.R. China Phone +86 755 2526-14540

Fax +86 755 2526-0974

E-Mail: sales@sundwiger-mw.com.cn

www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.