


## High-Performance Alloys SB21



Material Designation	
DIN-EN Symbol	CuNi1,5Si
DIN-EN	-
UNS	C19010
JIS	-
The Miller Company	-

Physical Properties		
Electrical conductivity soft	33.5	MS/m
Thermal conductivity	260	W/(m·K)
Thermal expansion coefficient **	17	10-6/K
Density	8.9	g/cm <sup>3</sup>
Modulus of elasticity	128	GPa = kN/mm <sup>2</sup>
Stress relaxation:		
H Temper condition up to	120	°C fair
TM Temper condition up to	140	°C fair

Nominal Composition (mass content in %)	
Cu	Balance
Ni	1.3
Si	0.35
Zn	0.2
Fe	< 0.1
Pb	< 0.005
P	0.015
Other	< 0.2


Typical Applications
<ul style="list-style-type: none"> <li>• Age-hardenable alloys for connectors and power transistor carriers and semiconductor devices</li> <li>• Leaf springs for relays</li> <li>• Stamped-bent parts</li> <li>• Transistor carriers</li> <li>• Connector pins</li> <li>• Carriers</li> <li>• Car electrics</li> </ul>

About The Alloy
<p>SB21 is an age-hardening CuNi1,5Si alloy for current-carrying formed parts on which particular requirements are placed.</p> <p>It has an <math>\alpha</math>-structure with very fine precipitations and recommends itself both for lead frames which require a high rigidity of the pins and for connectors with particularly high demands on the electrical conductivity with average strength and good relaxation behaviour.</p> <p>In addition, SB21 is also suitable for current-carrying formed parts and contact springs due to its good fatigue strength, forming and spring properties.</p> <p>The alloy is registered with the U.S. EPA as Antimicrobial.</p>

Mechanical Properties *)							
Temper condition		O R 360 H 100	H02 R 400 H 125	H03 R 460 H 135	H06 R 520 H 145	TM10 ** R 580 H 180	TM03 ** R 580S H 180S
Tensile strength in N/mm <sup>2</sup>		360 - 430	400 - 460	460 - 520	520 - 580	580 - 650	580 - 650
0.2 % yield Strength in N/mm <sup>2</sup>		250	350	430	470	540	540
Elongation A <sub>L50</sub> %		> 12	> 10	> 8	> 5	> 7	> 10
Vickers hardness HV		100 - 130	125 - 150	135 - 160	145 - 170	180 - 200	180 - 210
Electrical conductivity in % IACS		60	60	60	55	45	50
Minimum radius of the bending mandrel for 90° bend and strip thickness s							
0.10 ≤ s ≤ 0.25 mm	transverse	0 x s	0 x s	0 x s	0.5 x s	0.5 x s	0 x s
	parallel	0 x s	0.5 x s	0.5 x s	1.5 x s	1.5 x s	0.5 x s
0.25 < s ≤ 0.8 mm	transverse	0 x s	0 x s	0.5 x s	1.5 x s	-	1 x s
	parallel	0 x s	0.5 x s	1 x s	2.5 x s	-	1.5 x s

\*) Reference values    \*\*) mill aged

## High-Performance Alloys SB21



Processing Instructions	
Cold forming properties	very good
Machinability	satisfactory
Electroplating properties	good
Hot-dip tinning properties	good
Soldering	good
Resistance welding	good
Gas shielded arc welding	good
Laser welding	good

Available Dimensions	
Bright pre-rolled strips 1 to 2.5 mm	
Precision strip thickness from 0.05 to 1.2 mm	
Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness	
Other widths available on request.	

Available Versions	
Coils with standard outer diameters of 1200 mm	
Strips in reel form with coil weight of up to 1500 kg	
Multipancake up to 2.5 t	
Hot-dip tinned strips	
Profiled strips	
Electroplated strips (tin, nickel)	

Your Local Contact Person		
Europe	USA	Asia

### SUNDWIGER Messingwerk



### SUNDWIGER Messingwerk

<p>Sundwiger Messingwerk GmbH</p> <p>Hönnetalstraße 110 58675 Hemer Germany Phone +49 2372 661-0 Fax +49 2372 661-259 E-Mail: sales-sundwig@sundwiger-mw.com www.sundwiger-mw.com</p>	<p>The Miller Company</p> <p>275 Pratt Street CT 06450 Meriden USA Phone +1 203 63969-02 Fax +1 203 63969-24 E-Mail: sales@themillerco.com www.sundwiger-mw.com</p>	<p>Diehl Metall (Shenzhen) Co. Ltd.</p> <p>Block 25 Shatoujiao Free Trade Zone 518081 Shenzhen - P.R. China Phone +86 755 25261454-0 Fax +86 755 25260974 E-Mail: sales@sundwiger-mw.com.cn www.sundwiger-mw.com</p>
---	---	--

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.