## **SUNDWIGER** Messingwerk

# Bronze (Copper-Tin) **BB80**



Material Designation	
DIN-EN Symbol	CuSn8
DIN-EN	CW453K
UNS	C52100
JIS	C5212

'.5	MS/m
54	W/(m·K)
.8	10-6/K
3.8	g/cm³
.15	GPa = kN/mm²
	8

<sup>\*</sup> Reference values at room temperature

Nominal Composition (mass content in %)		
Cu	Balance	
Sn	8	
Zn	< 0.2	
Ni	< 0.2	
Fe	< 0.1	
Pb	< 0.005	
P	0.03 - 0.35	
Other	< 0.1	

#### **Typical Applications**

- Connectors for electrical engineering, electronics and automotive technology
- · Stamped-bent parts
- Contact springs
- · Leaf springs for relays
- Slide bearings
- Slide bars

### **About The Alloy**

BB80 is an 8 % tin bronze alloy which is distinguished by a very good combination of strength and electrical conductivity. It is used for connectors and current-carrying springs in contacts.

Among the 4 to 8 % tin bronze alloy BB80 exhibits the lowest electrical conductivity; the highest reachable strength is significantly higher than for BB40, BB50 and BB60. By means of an additional tempering after the cold forming process the bendability can be further improved.

The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.

Mechanical Properties *)							
Temper condition		O <b>R 370</b> H 90	H02 <b>R 450</b> H 140	H03 <b>R 540</b> H 170	H04 <b>R 600</b> H 190	H06 <b>R 660</b> H 210	H08 <b>R 735</b> H 230
Tensile strength in N/mm <sup>2</sup>		370 - 450	450 - 550	540 - 630	600 - 690	660 - 750	735 - 830
0.2 % yield Strength in N/n	nm²	< 300	380	470	540	620	700
Elongation A <sub>L50</sub> %		> 50	> 22	> 15	>8	> 6	> 2
Vickers hardness HV		90 - 120	140 - 175	170 - 200	190 - 220	210 - 240	230 - 260
Electrical conductivity in %	IACS	13	12	12	12	12	12
Minimum radius of the bending mandrel for 90° bend and strip thickness s, tempered quality							
0.10 ≤ s ≤ 0.25 mm	transver- se parallel	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	0 x s 1 x s	0.5 x s 1.5 x s	1 x s 4 x s
0.25 < s ≤ 1.0 mm	transver- se parallel	0 x s 0 x s	0 x s 0 x s	0 x s 0.5 x s	1 x s 2 x s	1 x s 3 x s	-

\*) Reference values

<sup>\*\*</sup> Between 20 and 300 °C



### Messingwerk

### Bronze (Copper-Tin) **BB80**



Processing Instructions	
Cold forming properties	very good
Machinability	sufficient
Electroplating properties	very good
Hot-dip tinning properties	very good
Soldering	very good
Resistance welding	good
Gas shielded arc welding	good
Laser welding	very good

	Dimer	

Bright pre-rolled strips 1 to 2.5 mm

Precision strip thickness from 0.05 to 1.2 mm

Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness

Other widths available on request.

#### **Available Versions**

Coils with standard outer diameters of 1200 mm

Strips in reel form with coil weight of up to 1500 kg

Multipancake up to 2.5 t

Hot-dip tinned strips

**Profiled strips** 

Electroplated strips (tin, nickel)

#### **Your Local Contact Person**

Europe

Asia

### **SUNDWIGER**

Messingwerk

**SUNDWIGER** 

Messingwerk

Sundwiger Messingwerk GmbH

Hönnetalstraße 110 58675 Hemer Deutschland

Tel. +49 2372 661-100 Fax +49 2372 661-48100

E-Mail: sales-sundwig@sundwiger-mw.com

www.sundwiger-mw.com

Diehl Metall (Shenzhen) Co. Ltd.

5F, Block 25, Shatoujiao Free Trade Zone

518081 Shenzhen P.R. of China

Tel. +86 755 2235 7466

Fax +86 755 25260974

E-Mail: sales@sundwiger-mw.com.cn

www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.