


Bronze (Copper-Tin) BB95 Ecobronze



Material Designation	
DIN-EN Symbol	(CuSn10)
DIN-EN	-
UNS	C52400
JIS	-

Physical Properties		
Electrical conductivity soft	6	MS/m
Thermal conductivity	50	W/(m·K)
Thermal expansion coefficient **	18.4	10 ⁻⁶ /K
Density	8.8	g/cm ³
Modulus of elasticity	110	GPa = kN/mm ²
* Reference values at room temperature		
** Between 20 and 300 °C		


Nominal Composition (mass content in %)	
Cu	Balance
Sn	10
Zn	< 0.2
Ni	< 0.2
Fe	< 0.1
Pb	< 0.005
p	0.03 - 0.35
Other	< 0.1

Typical Applications
<ul style="list-style-type: none"> • Connectors for electrical engineering, electronics and automotive technology • Stamped-bent parts • Contact springs • Leaf springs for relays • Slide bearings • Slide bars

About The Alloy
<p>The Ecobronze BB95 is an advanced 10 % tin bronze alloy to cope with the requirements of miniaturisation. BB95 is distinguished by a very good combination of strength and electrical conductivity. It is used for connectors and current-carrying springs in contacts.</p>
<p>Among the 4 to 10 % tin bronze alloys BB95 exhibits the lowest electrical conductivity; but the highest reachable strength is significantly higher than for BB40, BB50, BB60 and BB80. By means of an additional tempering after the cold forming process the bendability can be further improved.</p>
<p>The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.</p>

Mechanical Properties *)						
Temper condition		H04 R 650 H 200	H06 R 750 H 230	H08 R 850 H 240	H10 R 950 H 270	H12 R 1000 H 290
Tensile strength in N/mm ²		650 - 750	750 - 850	850 - 950	950 - 1050	> 1000
0.2 % yield Strength in N/mm ²		> 580	> 650	> 780	> 900	> 950
Elongation A _{LS0} %		> 11	> 9	> 5	> 1	-
Vickers hardness HV		200 - 240	230 - 270	250 - 290	270 - 310	> 290
Electrical conductivity in % IACS		10	10	10	10	10
Minimum radius of the bending mandrel for 90° bend and strip thickness s, tempered quality						
0.10 ≤ s ≤ 0.25 mm	transverse	0 x s	0 x s	1 x s	-	-
	parallel	0 x s	1.5 x s	2.5 x s	-	-
*) Reference values						

Bronze (Copper-Tin)
BB95
Ecobronze



Processing Instructions	
Cold forming properties	very good
Machinability	sufficient
Electroplating properties	very good
Hot-dip tinning properties	very good
Soldering	very good
Resistance welding	good
Gas shielded arc welding	good
Laser welding	very good

Available Dimensions
Bright pre-rolled strips 1 to 2.5 mm
Precision strip thickness from 0.05 to 1.2 mm
Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness
Other widths available on request.

Available Versions
Coils with standard outer diameters of 1200 mm
Strips in reel form with coil weight of up to 1500 kg
Multipancake up to 2.5 t
Hot-dip tinned strips
Profiled strips
Electroplated strips (tin, nickel)

Your Local Contact Person	
Europe	Asia
<p>SUNDWIGER Messingwerk</p> <p>Sundwiger Messingwerk GmbH</p> <p>Hönnetalstraße 110 58675 Hemer Deutschland Tel. +49 2372 661-100 Fax +49 2372 661-48100 E-Mail: sales-sundwig@sundwiger-mw.com www.sundwiger-mw.com</p>	<p>SUNDWIGER Messingwerk</p> <p>Diehl Metall (Shenzhen) Co. Ltd.</p> <p>5F, Block 25, Shatoujiao Free Trade Zone 518081 Shenzhen P.R. of China Tel. +86 755 2235 7466 Fax +86 755 25260974 E-Mail: sales@sundwiger-mw.com.cn www.sundwiger-mw.com</p>

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.