

Major changes start at the beginning:
Sundwiger ECO-SILVER 18 is the green starting point for the protection of our environment.

Carbon FoodPrint:
With the Recycling Input Rate of 97% the Primary Energy Consumption can be reduced by more than 40%. Concurrently, the Global Warming Potential is shortened by more than 50% (= net savings of more than 2.0 CO₂-Emission equivalents per kg)

Material Designation

DIN-EN Symbol	CuNi18Zn20
DIN-EN	CW409J
UNS	≈ C 76400
JIS	C7521

Nominal Composition (mass content in %)

Cu	Balance
Ni	18
Zn	20
Fe	< 0.2
Mn	< 0.25
Sn	< 0.03
Pb	< 0.005
Cd	< 0.002
Other	< 0.08

Typical Applications

- Coins, caps for quartz crystals
- Electromagnetic shieldings
- Deep drawing parts
- Tableware, security keys, cutlery
- Contact springs, connector, leaf springs for relays, electric contacts

About The Alloy

Sundwiger ECO-SILVER 18 has been developed in response to the demand of numerous customers for an environmentally sound alternative alloy to C7521. Having a significant positive impact on the environment by reducing the carbon footprint, this material has also a guaranteed and certified RIR potential of at least 97%.

The RIR (Recycling Input Rate) is measured according to the environmental standard, which excludes primary metals and home scrap.

Sundwiger ECO-SILVER 18 has good cold-forming properties, is tarnish resistant and has very good spring properties. Like all copper alloys the copper-nickel-zinc alloys are not susceptible to embrittlement at lower temperature. The corrosion resistance of nickel silver is considerably better than that of binary copper-zinc alloys. Sundwiger ECO-SILVER 18 is insensitive to stress corrosion cracking.

Physical Properties*

Electrical conductivity soft	3	MS/m
Thermal conductivity	27	W/(m·K)
Thermal expansion coefficient **	17	10 ⁻⁶ /K
Density	8.7	g/cm ³
Modulus of elasticity	135	GPa = kN/mm ²

* Reference values

** Between 20 and 300 °C

Mechanical Properties *)

Temper condition		0 R 380 H 90	H02 R 450 H 115	H04 R 540 H 160
Tensile strength in N/mm ² (for reference only)		380 - 480	450 - 550	540 - 640
0.2% yield strength in N/mm ² (for reference only)		< 290	250	450
Elongation A _{L50} % (for reference only)		> 30	> 25	> 15
Vickers hardness HV (for binding)		90 - 130	125 - 160	160 - 195
Electrical conductivity in % IACS		5	4	4
Minimum radius of the bending mandrel for 90° bend and strip thickness s				
0.10 ≤ s ≤ 0.25 mm	transverse	0 x s	0 x s	0 x s
	parallel	0 x s	0 x s	0 x s
0.25 < s ≤ 1.0 mm	transverse	0 x s	0 x s	0 x s
	parallel	0 x s	0 x s	0 x s

*) Reference values

Processing Instructions

Cold forming properties	Machinability	Electroplating properties	Hot-dip tinning properties	Soldering	Resistance welding	Gas shielded arc welding	Laser welding
very good	satisfactory	very good	good	good	very good	good	good

Available Dimensions

Bright pre-rolled strips 1 to 2.5 mm

Precision strip thickness from 0.05 to 1.2 mm

Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness

Other widths available on request.

Available Versions

Coils with standard outer diameters of 1200 mm

Strips in reel form with coil weight of up to 1500 kg

Multipancake up to 2.5 t

Hot-dip tinned strips

Profiled strips

Electroplated strips (tin, nickel)

Your Local Contact Person

Europe

Asia

SUNDWIGER
Messingwerk

SUNDWIGER
Messingwerk

Sundwiger Messingwerk GmbH

Diehl Metall (Shenzhen) Co. Ltd.

Hönnetalstraße 110
58675 Hemer
Deutschland
Tel. +49 2372 661-100
Fax +49 2372 661-48100
E-Mail: sales-sundwig@sundwiger-mw.com
www.sundwiger-mw.com

5F, Block 25, Shatoujiao Free Trade Zone
518081 Shenzhen
P.R. of China
Tel. +86 755 2235 7466
Fax +86 755 25260974
E-Mail: sales@sundwiger-mw.com.cn
www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability.