SUNDWIGER Messingwerk

Nickel Silver NB12



Material Designation			
DIN-EN Symbol	CuNi12Zn24		
DIN-EN	CW403J		
UNS	C75700		
JIS	-		

Physical Properties				
Electrical conductivity soft	4	MS/m		
Thermal conductivity	33	W/(m·K)		
Thermal expansion coefficient **	17	10-6/K		
Density	8.7	g/cm³		
Modulus of elasticity	125	GPa = kN/mm ²		

^{*} Reference values at room temperature

Nominal Composition (mass content in %)		
Cu	Balance	
Ni	12	
Zn	24	
Fe	< 0.2	
Mn	< 0.5	
Pb	< 0.01	
Other	< 0.2	

Typical Applications

- Coins
- Caps for quartz crystals
- Electromagnetic shieldings
- Deep drawing parts
- Tableware
- · Security keys
- Cutlery
- Contact springs
- Connector
- Leaf springs for relays
- Electric contacts

About The Alloy

NB12 is a nickel silver alloy containing 12 % nickel and 24 % zinc.

The alloy has good cold-forming properties and is particularly suitable for deepdrawing.

Like all copper alloys the copper-nickel-zinc alloys are not susceptible to embrittlement at lower temperature. The corrosion resistance of nickel silver is considerably better than that of binary copper-zinc alloys.

NB12 is insensitive to stress corrosion cracking. NB12 is used for contacts, deepdrawing parts and for optical goods.

The alloy is registered with the U.S. EPA as Antimicrobial.

Mechanical Properties *)						
Temper condition		O R 350 H 80	H02 R 430 H 110	H03 R 490 H 140	H04 R 550 H 170	H06 R 620 H 190
Tensile strength in N/mm ²		350 - 450	430 - 510	490 - 580	550 - 640	620 - 710
0.2 % yield Strength in N/mm²		200	230	400	480	580
Elongation A _{L50} %		> 35	>8	> 7	>3	-
Vickers hardness HV		80 - 110	110 - 150	150 - 180	170 - 200	190 - 220
Electrical conductivity in %	IACS	7	7	6	6	6
Minimum radius of the bending mandrel for 90° bend and strip thickness s						
0.10 ≤ s ≤ 0.25 mm	transverse parallel	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	1 x s 2 x s
0.25 < s ≤ 1.0 mm	transverse parallel	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	0 x s 1 x s	-
*) Reference values						

^{**} Between 20 and 300 °C



Nickel Silver NB12



Processing Instructions		
Cold forming properties	very good	
Machinability	satisfactory	
Electroplating properties	very good	
Hot-dip tinning properties	satisfactory	
Soldering	satisfactory	
Resistance welding	very good	
Gas shielded arc welding	good	
Laser welding	good	

Available Dimensions

Bright pre-rolled strips 1 to 2.5 mm

Precision strip thickness from 0.05 to 1.2 mm

Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness

Other widths available on request.

Available Versions

Coils with standard outer diameters of 1200 mm

Strips in reel form with coil weight of up to 1500 kg

Multipancake up to 2.5 t

Hot-dip tinned strips

Profiled strips

Electroplated strips (tin, nickel)

Your Local Contact Person

Europe

Asia

SUNDWIGER

Messingwerk

SUNDWIGER

Messingwerk

Sundwiger Messingwerk GmbH

Hönnetalstraße 110

58675 Hemer

Deutschland

Tel. +49 2372 661-100

Fax +49 2372 661-48100

E-Mail: sales-sundwig@sundwiger-mw.com

www.sundwiger-mw.com

Diehl Metall (Shenzhen) Co. Ltd.

5F, Block 25, Shatoujiao Free Trade Zone

518081 Shenzhen

P.R. of China

Tel. +86 755 2235 7466

Fax +86 755 25260974

E-Mail: sales@sundwiger-mw.com.cn

www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.