



## High-Performance Alloys SB92



Material Designation			Nominal Composition (mass content in %)		About The Alloy															
DIN-EN Symbol	CuNi9Sn2		Cu	Balance		<p>SB92 is a cupro-nickel 10 material to which approx. 2 % tin is added. It is mainly used for spring-action parts.</p> <p>SB92 is distinguished by a very good stress relaxation behaviour in spring hard condition, a good tarnish resistance as well as a high softening temperature. By means of an additional tempering after the cold forming process the bendability can be considerably improved.</p> <p>The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.</p>														
DIN-EN	CW351H		Ni	9.5																
UNS	C72500		Sn	2.3																
JIS	C7250		Fe	< 0.3																
<b>Physical Properties</b>			Mn	< 0.2																
			Zn	< 0.1																
			Pb	< 0.005																
			Other	< 0.1																
			<b>Typical Applications</b> <ul style="list-style-type: none"> <li>• Age-hardenable alloys for connectors and power transistor carriers and semiconductor devices</li> <li>• Leaf springs for relays</li> <li>• Stamped-bent parts</li> <li>• Transistor carriers</li> <li>• Connector pins</li> <li>• Carriers</li> <li>• Car electrics</li> </ul>				<table border="1"> <tr> <td>Electrical conductivity soft</td> <td>6</td> <td>MS/m</td> </tr> <tr> <td>Thermal conductivity</td> <td>120</td> <td>W/(m·K)</td> </tr> <tr> <td>Thermal expansion coefficient **</td> <td>17.2</td> <td>10<sup>-6</sup>/K</td> </tr> <tr> <td>Density</td> <td>8.9</td> <td>g/cm<sup>3</sup></td> </tr> <tr> <td>Modulus of elasticity</td> <td>140</td> <td>GPa = kN/mm<sup>2</sup></td> </tr> </table>		Electrical conductivity soft	6	MS/m	Thermal conductivity	120	W/(m·K)	Thermal expansion coefficient **	17.2	10 <sup>-6</sup> /K	Density	8.9	g/cm <sup>3</sup>
Electrical conductivity soft	6	MS/m																		
Thermal conductivity	120	W/(m·K)																		
Thermal expansion coefficient **	17.2	10 <sup>-6</sup> /K																		
Density	8.9	g/cm <sup>3</sup>																		
Modulus of elasticity	140	GPa = kN/mm <sup>2</sup>																		
* Reference values at room temperature ** Between 20 and 300 °C																				

Mechanical Properties *)							
Temper condition		O R 340 H 80	H01 R 380 H 110	H02 R 450 H 140	H04 R 500 H 160	H06 R 560 H 180	H08 R 610 H 190
Tensile strength in N/mm <sup>2</sup>		340 - 410	380 - 480	450 - 540	500 - 580	560 - 650	610 - 700
0.2 % yield Strength in N/mm <sup>2</sup>		< 250	300	370	450	520	580
Elongation A <sub>LS0</sub> %		> 30	> 10	> 6	> 3	> 2	-
Vickers hardness HV		80 - 110	110 - 150	140 - 170	160 - 190	180 - 210	190 - 220
Electrical conductivity in % IACS		10	10	10	10	10	10
Minimum radius of the bending mandrel for 90° bend and strip thickness s							
0.10 ≤ s ≤ 0.25 mm	transverse	0 x s	0 x s	0 x s	0 x s	1 x s	3 x s
	parallel	0 x s	0 x s	0 x s	0 x s	3 x s	7 x s
0.25 < s ≤ 1.0 mm	transverse	0 x s	0 x s	0 x s	0.5 x s	2 x s	-
	parallel	0 x s	0 x s	0.5 x s	1 x s	5 x s	-
*) Reference values							

## High-Performance Alloys SB92



Processing Instructions	
Cold forming properties	very good
Machinability	sufficient
Electroplating properties	good
Hot-dip tinning properties	good
Soldering	good
Resistance welding	very good
Gas shielded arc welding	very good
Laser welding	very good

Available Dimensions
Bright pre-rolled strips 1 to 2.5 mm
Precision strip thickness from 0.05 to 1.2 mm
Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness
Other widths available on request.

Available Versions
Coils with standard outer diameters of 1200 mm
Strips in reel form with coil weight of up to 1500 kg
Multipancake up to 2.5 t
Hot-dip tinned strips
Profiled strips
Electroplated strips (tin, nickel)

Your Local Contact Person	
Europe	Asia
<p><b>SUNDWIGER</b> Messingwerk</p> <p>Sundwiger Messingwerk GmbH</p> <p>Hönnetalstraße 110 58675 Hemer Deutschland Tel. +49 2372 661-100 Fax +49 2372 661-48100 E-Mail: sales-sundwig@sundwiger-mw.com www.sundwiger-mw.com</p>	<p><b>SUNDWIGER</b> Messingwerk</p> <p>Diehl Metall (Shenzhen) Co. Ltd.</p> <p>5F, Block 25, Shatoujiao Free Trade Zone 518081 Shenzhen P.R. of China Tel. +86 755 2235 7466 Fax +86 755 25260974 E-Mail: sales@sundwiger-mw.com.cn www.sundwiger-mw.com</p>

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.