

## BB40 Plus - CuSn4

Material Designation	
DIN-EN Symbol	(CuSn4+)
DIN-EN	CW450K
UNS	C51100
JIS	C5111

Physical Properties		
Electrical conductivity soft	12	MS/m
Thermal conductivity	86	W/(m·K)
Thermal expansion coefficient **	17	10-6/K
Density	8,9	g/cm³
Modulus of elasticity	120	GPa = kN/mm²
* Reference values at room ter	nperatur	e

Nominal Composition (mass content in %)	
Cu	Balance
Sn	4
Zn	< 0,2
Ni	< 0,2
Fe	< 0,1
Pb	< 0,005
P	0,03 - 0,35
Other	< 0,1
Typical Applications	

- Connectors for electrical engineering, electronics and automotive technology
- Stamped-bent parts
- **Contact springs**
- Leaf springs for relays
- Slide bearings
- Slide bars

## **About The Alloy**

The Ecobronze BB40 Plus is a modified 4 % tin bronze which is distinguished by a very fine structure with considerably higher strength and elongation and a high electrical conductivity.

It is used for miniaturized connectors and current-carrying springs in contacts.

Among the 4 to 8 % tin bronzes BB40 Plus exhibits the highest electrical conductivity. Regarding the strength it reaches the level of a standard 6 % bronze.

The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.

Mechanical Properties *)					
Temper condition		H06S <b>R 600S</b> H 190S	H08S <b>R 660S</b> H 200S	H10S <b>R 700S</b> H 210S	H12S <b>R 750S</b> H 220S
Tensile strength in N/mm <sup>2</sup>		600 - 680	660 - 720	700 - 800	750 - 840
0.2 % yield strength in N/m	ım²	560	625	660	720
Elongation A <sub>L50</sub> %		> 13	> 7	> 5	> 2
Vickers hardness HV		190 - 220	200 - 230	210 - 240	220 - 245
Electrical conductivity in %	IACS	20	20	20	20
Minimum radius of the bending mandrel for 90° bend and strip thickness s with a thickness/width ratio of < 10					
0.10 ≤ s ≤ 0.25 mm	transverse parallel	0 x s 1 x s	0 x s 2 x s	0.5 x s 3 x s	1 x s 4 x s
*) Reference values					

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.

<sup>\*\*</sup> Between 20 and 300 °C



## BB40 Plus - CuSn4

Other widths available on request

Processing Instructions	
Cold forming properties	very good
Machinability	sufficient
Electroplating properties	very good
Hot-dip tinning properties	very good
Soldering	very good
Resistance welding	good
Gas shielded arc welding	good
Laser welding	very good

Available Versions
Coils with standard outer diameters of 1200 mm
Strips in reel form with coil weight of up to 1500 kg
Multipancake up to 2.5 t
Hot-dip tinned strips
Profiled strips
Electroplated strips (tin, nickel)

Your Local Contact Person	
Europe	Asia



Messiii	gwerk
Sundwiger Messingwerk GmbH	Sundwiger Metal (Shenzhen) Co. Ltd.
Hönnetalstraße 110 58675 Hemer Deutschland Tel. +49 2372 661-100 Fax +49 2372 661-48100 E-Mail: sales-sundwig@sundwiger-mw.com	5F, Block 25, Shatoujiao Free Trade Zone 518081 Shenzhen P.R. of China Tel. +86 755 2235 7466 Fax +86 755 25260974 E-Mail: sales@sundwiger-mw.com.cn
www.sundwiger-mw.com	www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.