Special Alloys (Machinable Bronzes) . BY44 | BY51 |



| Material Designation | | |
|----------------------|-------------|----------|
| Sundwiger | BY44 | BY51 |
| DIN-EN Symbol | CuSn4Zn4Pb4 | CuSn5Pb1 |
| DIN-EN | CW456K | CW458K |
| UNS | C54400 | C53400 |
| JIS | C5441 | C5341 |

| Physical Properties* | | | |
|---|------------|-------------|---------------------|
| Sundwiger | BY44 | BY51 | |
| Electrical conductivity | ≥11 ≥19 | ≥9.8 ≥17 | MS/m % IACS |
| Thermal conductivity | 80 | 80 | W/(m·K) |
| Thermal expansion coefficient** | 17 | 17 | 10 ⁻⁶ /K |
| Density | 8.8 | 8.8 | g/cm³ |
| Modulus of elasticity | 118 | 117 | GPa = kN/mm² |
| Machinability index compared to CuZn39Pb3 | 90 | 60 | % |
| * Reference values at room temperature | | | |

| Mechanical Properties* | | |
|--|-------|-------|
| Sundwiger | BY44 | BY51 |
| Tensile strength in N/mm², soft | ≤ 450 | ≤ 450 |
| Elongation A100 in %, soft | 8 | 8 |
| Tensile strength in N/mm², hard | ≥ 720 | ≥ 720 |
| * Reference values at room temperature | | |

Your Contact Person

* Between 20 and 300 °C

Worldwide

Sundwiger Messingwerk GmbH Hönnetalstraße 110 58675 Hemer Deutschland Tel. +49 2372 661-0 Fax +49 2372 661-259

E-Mail: sales-sundwig@sundwiger-mw.com

www.sundwiger-mw.com

About the Alloy

BY44 is a leaded multi-component bronze which shows very good machinability and good corrosion resistance. It is also distinguished by its excellent spring properties.

BY44 is used for electrical contacts that need to be manufactured as turned parts. BY44 can be drawn over 800N/mm², which makes it significantly stronger than leaded brass materials. Compared with leaded brass materials, BY44 is resistant to stress-corrosion cracking.

BY51 offers – like a conventional bronze – good cold forming properties and good corrosion resistance in addition to moderate machinability.

BY51 is used in electrical engineering and in the automotive industry for various applications. While the desired tensile strength is adjusted by cold forming, the shape of the component can be produced by machining. Compared with leaded brass materials, BY51 is also resistant to stress-corrosion cracking.

| Reference to | Standards |
|--------------|-----------|
| DIN | EN 12166 |

Typical Applications

Available Dimensions

- Turned contact elements
- Pins

| Nominal Composition (mass content in %) | | |
|---|---------|---------|
| Sundwiger | BY44 | BY51 |
| Cu | Balance | Balance |
| Sn | 4 | 5 |
| Zn | 4 | < 0,3 |
| Pb | 4 | 1 |
| Fe | < 0,1 | < 0,1 |
| Р | 0,4 | 0,4 |
| Others | < 0,2 | < 0,4 |

| Round wire | 1,2 - 6,2 mm in coils | max. 200 kg |
|---------------|---|--------------|
| | 1,8 - 6,2 mm on stands | max. 1500 kg |
| | 0,5 - 3 mm on reels | max. 1000 kg |
| | 1,5 - 3 mm on acropaks | max. 400 kg |
| | On request: in drums | max. 400 kg |
| | On request: 2 - 5 mm in bars, sheared ends (length ≤ 3.5 m) | max. 500 kg |

SUNDWIGER Messingwerk

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability.

Please ask for the latest edition of this material data sheet.