

# NB18 - CuNi18Zn20

Material Designation	
DIN-EN Symbol	CuNi18Zn20
DIN-EN	CW409J
UNS	~ C76400
JIS	C7521

Physical Properties		
Electrical conductivity soft	3	MS/m
Thermal conductivity	27	W/(m·K)
Thermal expansion coefficient **	17	10-6/K
Density	8,7	g/cm³
Modulus of elasticity	135	GPa = kN/mm²

<sup>\*</sup> Reference values at room temperature

Nominal Composition
(mass content in %)

Cu	Balance
Ni	18
Zn	20
Fe	< 0,2
Mn	< 0,5
Pb	< 0,01
Other	< 0,2

#### **Typical Applications**

- · Coins
- Caps for quartz crystals
- Electromagnetic shieldings
- Deep drawing parts
- . Tableware
- Security keys
- Cutlery
- Contact springs
- Connector
- · Leaf springs for relays
- Electric contacts

## **About The Alloy**

NB18 is a nickel silver alloy containing 18 % nickel and 20 % zinc. The alloy has good cold-forming properties, is tarnish resistant and has very good spring properties.

Like all copper alloys the copper-nickelzinc alloys are not susceptible to embrittlement at lower temperature. The corrosion resistance of nickel silver is

considerably better than that of binary copper-zinc alloys.

NB18 is insensitive to stress corrosion cracking. NB18 is used for contact springs in relays, EMI shieldings and jewelry.

Mechanical Properties	*)					
Temper condition		O <b>R 370</b> H 85	H02 <b>R 450</b> H 115	H04 <b>R 500</b> H 160	H06 <b>R 580</b> H 180	H08 <b>R 640</b> H 200
Tensile strength in N/mr	n²	370 - 460	450 - 520	500 - 590	580 - 680	640 - 730
0.2 % yield Strength in N	J/mm²	< 250	250	410	510	600
Elongation A <sub>L50</sub> %		> 30	> 9	> 3	> 2	-
Vickers hardness HV		85 - 125	115 - 160	160 - 190	180 - 210	200 - 230
Electrical conductivity in	% IACS	5	4	4	4	4
Minimum radius of the bending mandrel for 90° bend and strip thickness s						
0.10 ≤ s ≤ 0.25 mm	transverse parallel	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s
0.25 < s ≤ 1.0 mm	transverse parallel	0 x s 0 x s	0 x s 0 x s	0 x s 0 x s	0 x s 1 x s	-
*) Reference values						

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.

<sup>\*\*</sup> Between 20 and 300 °C



## NB18 - CuNi18Zn20

Processing Instructions	
Cold forming properties	very good
Machinability	satisfactory
Electroplating properties	very good
Hot-dip tinning properties	satisfactory
Soldering	satisfactory
Resistance welding	very good
Gas shielded arc welding	good
Laser welding	good

Available Versions
Coils with standard outer diameters of 1200 mm
Strips in reel form with coil weight of up to 1500 kg
Multipancake up to 2.5 t
Hot-dip tinned strips
Profiled strips
Electroplated strips (tin, nickel)

### **Available Dimensions**

Bright pre-rolled strips 1 to 2.5 mm

Precision strip thickness from 0.05 to 1.2 mm

Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness

Other widths available on request

#### **Your Local Contact Person** Europe Asia

# SUNDWIGER Messingwerk

Sundwiger Messingwerk GmbH

Sundwiger Metal (Shenzhen) Co. Ltd.

Hönnetalstraße 110 58675 Hemer Deutschland Tel. +49 2372 661-100

Fax +49 2372 661-48100

E-Mail: sales-sundwig@sundwiger-

mw.com

www.sundwiger-mw.com

5F, Block 25, Shatoujiao Free Trade Zone

518081 Shenzhen P.R. of China

Tel. +86 755 2235 7466 Fax +86 755 25260974

E-Mail: sales@sundwiger-mw.com.cn

www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.