

SB01 – CuFe0,1P

Material Designation			Nominal Composition (mass content in %)		About The Alloy
DIN-EN Symbol	CuFe0,1P		Cu	Balance	
DIN-EN	-		Fe	0,1	
UNS	C19210		P	0,03	
JIS	C1921		Other	< 0,1	
Physical Properties			Typical Applications		<p>Low-alloyed copper alloys are distinguished by a high electrical conductivity. They do not reach the spring force of the bronzes, however, in comparison with pure copper, they are significantly harder. Therefore, they are predominantly used for lead frames for semiconductors.</p> <p>SB01 is a copper alloy with a very low iron content. SB01 differs from SB02 (UNS C19400) by the higher thermal conductivity and the higher electrical conductivity. In comparison with pure copper SB01 has a higher strength while the electrical conductivity is a little lower. SB01 has excellent soldering and welding properties.</p> <p>The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.</p>
Electrical conductivity soft	49	MS/m	<ul style="list-style-type: none">• Age-hardenable alloys for connectors and power transistor carriers and semiconductor devices• Leaf springs for relays• Stamped-bent parts• Transistor carriers• Connector pins• Carriers• Car electrics		
Thermal conductivity	430	W/(m·K)			
Thermal expansion coefficient **	17	10-6/K			
Density	8,9	g/cm³			
Modulus of elasticity	125	GPa = kN/mm²			
* Reference values at room temperature					
** Between 20 and 300 °C					

Mechanical Properties *)						
Temper condition		O R 300 H 80	H02 R 360 H 100	H04 R 390 H 110	H06 R 415 H 130	H08 R 450 H 130
Tensile strength in N/mm ²		300 - 380	360 - 440	390 - 450	415 - 480	450 - 520
0.2 % yield Strength in N/mm ²		< 300	280	330	380	430
Elongation A _{L50} %		> 10	> 6	> 3	> 3	> 2
Vickers hardness HV		80 - 110	100 - 130	110 - 140	120 - 145	130 - 160
Electrical conductivity in % IACS		85	85	84	84	84
Minimum radius of the bending mandrel for 90° bend and strip thickness s, tempered quality						
0.10 ≤ s ≤ 0.25 mm	transverse	0 x s	0 x s	1 x s	1 x s	1.5 x s
	parallel	0 x s	0 x s	1 x s	1 x s	1.5 x s
0.25 < s ≤ 0.5 mm	transverse	0 x s	0 x s	1 x s	1 x s	-
	parallel	0 x s	0 x s	1 x s	1.5 x s	-
*) Reference values						

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.

Processing Instructions

Cold forming properties	very good
Machinability	sufficient
Electroplating properties	very good
Hot-dip tinning properties	very good
Soldering	very good
Resistance welding	good
Gas shielded arc welding	good
Laser welding	very good

Available Versions

Coils with standard outer diameters of 1200 mm
Strips in reel form with coil weight of up to 1500 kg
Multipancake up to 2.5 t
Hot-dip tinned strips
Profiled strips
Electroplated strips (tin, nickel)

Available Dimensions

Bright pre-rolled strips 1 to 2.5 mm
Precision strip thickness from 0.05 to 1.2 mm
Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness
Other widths available on request

Your Local Contact Person

Europe

Asia



Sundwiger Messingwerk GmbH

Hönnetalstraße 110
58675 Hemer
Deutschland
Tel. +49 2372 661-100
Fax +49 2372 661-48100
E-Mail: sales-sundwig@sundwiger-mw.com
www.sundwiger-mw.com

Sundwiger Metal (Shenzhen) Co. Ltd.

5F, Block 25, Shatoujiao Free Trade Zone
518081 Shenzhen
P.R. of China
Tel. +86 755 2235 7466
Fax +86 755 25260974
E-Mail: sales@sundwiger-mw.com.cn
www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.