

Material Designation			Nominal Composition (mass content in %)		About The Alloy	
DIN-EN Symbol	CuFe2P		Cu	Balance	Low-alloyed copper alloys are distinguished by a high electrical conductivity. They do not reach the spring force of the bronzes, however, in comparison with pure copper, they are significantly harder.	
DIN-EN	CW107C		Fe	2,4		
UNS	C19400		Zn	0,13		
JIS	C1940		Pb	< 0,005		
			P	0,03		
Physical Properties			Other	< 0,1	During the last decade SB02 (UNS C19400) has gained importance for lead frames because of the high electrical conductivity and the favourable price and in the meantime it has become the copper alloy with the world-wide most frequent use for this application. Due to the necessary miniaturisation of components and the increased packing density involved, materials with high conductivity gain importance. Therefore, for some time SB02 is also used in electric and electronic automotive applications for special connectors and for the central fuse, relay and terminal box.	
Electrical conductivity soft	36,5	MS/m	Typical Applications			The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.
Thermal conductivity	260	W/(m·K)				
Thermal expansion coefficient **	17	10-6/K				
Density	8,9	g/cm³				
Modulus of elasticity	123	GPa = kN/mm²				
* Reference values at room temperature ** Between 20 and 300 °C						
			<ul style="list-style-type: none"><li>• Age-hardenable alloys for connectors and power transistor carriers and semiconductor devices</li><li>• Leaf springs for relays</li><li>• Stamped-bent parts</li><li>• Transistor carriers</li><li>• Connector pins</li><li>• Carriers</li><li>• Car electrics</li></ul>			

Mechanical Properties *)							
Temper condition		O R 300 H 80	H01 R 340 H 100	H02 R 370 H 110	H04 R 415 H 125	H08 R 480 H 140	H10 R 530 H 150
Tensile strength in N/mm <sup>2</sup>		300 - 340	340 - 390	370 - 430	415 - 480	480 - 525	530 - 570
0.2 % yield Strength in N/mm <sup>2</sup>		< 240	240	330	380	440	470
Elongation A <sub>L50</sub> %		> 20	> 10	> 6	> 4	> 3	> 3
Vickers hardness HV		80 - 100	100 - 120	110 - 140	125 - 145	140 - 160	150 - 170
Electrical conductivity in % IACS		63	62	60	60	60	60
Minimum radius of the bending mandrel for 90° bend and strip thickness s, tempered quality							
0.10 ≤ s ≤ 0.25 mm	transverse	0 x s	0 x s	0 x s	0.5 x s	0.5 x s	1 x s
	parallel	0 x s	0 x s	0 x s	0.5 x s	1 x s	1.5 x s
0.25 < s ≤ 0.5 mm	transverse	0 x s	0 x s	0 x s	1 x s	1 x s	1.5 x s
	parallel	0 x s	0 x s	0 x s	1 x s	2 x s	3 x s
*) Reference values							

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.

### Processing Instructions

Cold forming properties	very good
Machinability	sufficient
Electroplating properties	very good
Hot-dip tinning properties	very good
Soldering	very good
Resistance welding	good
Gas shielded arc welding	good
Laser welding	good

### Available Versions

Coils with standard outer diameters of 1200 mm
Strips in reel form with coil weight of up to 1500 kg
Multipancake up to 2.5 t
Hot-dip tinned strips
Profiled strips
Electroplated strips (tin, nickel)

### Available Dimensions

Bright pre-rolled strips 1 to 2.5 mm
Precision strip thickness from 0.05 to 1.2 mm
Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness
Other widths available on request

### Your Local Contact Person

Europe

Asia



Sundwiger Messingwerk GmbH

Hönnetalstraße 110  
58675 Hemer  
Deutschland  
Tel. +49 2372 661-100  
Fax +49 2372 661-48100  
E-Mail: sales-sundwig@sundwiger-mw.com  
www.sundwiger-mw.com

Sundwiger Metal (Shenzhen) Co. Ltd.

5F, Block 25, Shatoujiao Free Trade Zone  
518081 Shenzhen  
P.R. of China  
Tel. +86 755 2235 7466  
Fax +86 755 25260974  
E-Mail: sales@sundwiger-mw.com.cn  
www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.