

Material Designation

DIN-EN Symbol	CuNi2Si
DIN-EN	CW111C
UNS	C70260 / C64700
JIS	-

Physical Properties

Electrical conductivity soft	32	MS/m
Thermal conductivity	250	W/(m·K)
Thermal expansion coefficient **	17	10 ⁻⁶ /K
Density	8,8	g/cm ³
Modulus of elasticity	130	GPa = kN/mm ²
Stress relaxation:		
H Temper condition up to	125	°C fair
TM Temper condition up to	150	°C fair

* Reference values at room temperature

** Between 20 and 300 °C

Nominal Composition
(mass content in %)

Cu	Balance
Ni	1,9
Si	0,5
Zn	0,3
Fe	< 0,1
Pb	< 0,005
P	0,01
Other	< 0,1

Typical Applications

- Age-hardenable alloys for connectors and power transistor carriers and semiconductor devices
- Leaf springs for relays
- Stamped-bent parts
- Transistor carriers
- Connector pins
- Carriers
- Car electrics

About The Alloy

SB22 is an age-hardening CuNi2Si alloy, higher alloyed in comparison with SB21, for current-carrying formed parts.

It has an α -structure with very fine precipitations and recommends itself both for lead frames which require a high rigidity of the pins and for connectors with high demands on the electrical conductivity, strength, thermal load and relaxation behaviour.

In addition, SB22 can also be used for current-carrying formed parts and contact springs due to its good fatigue strength, forming and spring properties.

The alloy is registered with the U.S. EPA as Antimicrobial.

Mechanical Properties *)

Temper condition	O R 360 H 100	H02 R 420 H 130	H03 R 460 H 140	TM00 ** R 580 H 170	TM10 ** R 600 H 180	TM03 ** R 620 H 190
Tensile strength in N/mm ²	360 - 430	420 - 480	460 - 530	580 - 650	600 - 670	620 - 690
0.2 % yield Strength in N/mm ²	250	380	430	470	570	580
Elongation A _{L50} %	> 12	> 9	> 7	> 12	> 7	> 10
Vickers hardness HV	100 - 130	130 - 150	140 - 160	170 - 200	180 - 220	190 - 220
Electrical conductivity in % IACS	55	55	55	45	40	48

Minimum radius of the bending mandrel for 90° bend and strip thickness s,

0.10 ≤ s ≤ 0.25 mm	transverse parallel	0 x s 0 x s	0 x s 0.5 x s	0 x s 0.5 x s	0 x s 0.5 x s	0.5 x s 1 x s	0 x s 1 x s
0.25 < s ≤ 0.8 mm	transverse parallel	0 x s 0 x s	0 x s 0.5 x s	0.5 x s 1 x s	0.5 x s 1 x s	- -	1 x s 1.5 x s

*) Reference values ***) mill aged

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.

Processing Instructions

Cold forming properties	very good
Machinability	sufficient
Electroplating properties	good
Hot-dip tinning properties	good
Soldering	good
Resistance welding	good
Gas shielded arc welding	good
Laser welding	good

Available Versions

Coils with standard outer diameters of 1200 mm
Strips in reel form with coil weight of up to 1500 kg
Multipancake up to 2.5 t
Hot-dip tinned strips
Profiled strips
Electroplated strips (tin, nickel)

Available Dimensions

Bright pre-rolled strips 1 to 2.5 mm
Precision strip thickness from 0.05 to 1.2 mm
Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness
Other widths available on request

Your Local Contact Person

Europe

Asia



Sundwiger Messingwerk GmbH

Hönnetalstraße 110
58675 Hemer
Deutschland
Tel. +49 2372 661-100
Fax +49 2372 661-48100
E-Mail: sales-sundwig@sundwiger-mw.com
www.sundwiger-mw.com

Sundwiger Metal (Shenzhen) Co. Ltd.

5F, Block 25, Shatoujiao Free Trade Zone
518081 Shenzhen
P.R. of China
Tel. +86 755 2235 7466
Fax +86 755 25260974
E-Mail: sales@sundwiger-mw.com.cn
www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.