## Copper Magnesium SD01 | SD02 | SD03 | SD04 | SD05 |



| Material Designation |           |         |                  |           |         |
|----------------------|-----------|---------|------------------|-----------|---------|
| Sundwiger            | SD01      | SD02    | SD03             | SD04      | SD05 *  |
| DIN-EN Symbol        | (CuMg0,1) | CuMg0,2 | CuMg0,3          | (CuMg0,4) | CuMg0,5 |
| DIN-EN               | CW127C    | CW127C  | CW127C<br>CW128C | CW128C    | CW128C  |
| UNS                  |           | C18661  |                  | C18661/   | C18665  |

<sup>\*</sup> Symbol for contact wire

#### **Typical Applications**

- Conductor wire
- Connector wirePins
- Telecommunications cable
  Catanany cables
- · Catenary cables
- Contact wire for high-speed trains

| Physical Properties*  |       |       |       |                   |
|---|-------|-------|-------|-------------------|
| Sundwiger   | SD01  | SD02  | SD03  | SD04 /<br>SD05 ** |
| Electrical conductivity in % IACS (hard condition)                  | ≥80   | ≥77   | ≥72   | ≥64               |
| Electrical conductivity in MS/m                                     | ≥46.4 | ≥44.6 | ≥41.7 | ≥37.1             |
| Thermal conductivity in W/(m*K)                                     | 310   | 310   | 290   | 250               |
| Density in g/cm <sup>3</sup>  | 8.9   | 8.9   | 8.9   | 8.9               |
| * Reference values at room temperature   ** Symbol for contact wire |       |       |       |                   |

| Mechanical Properties* |       |       |       |
|------------------------|-------|-------|-------|
|                        | 65.04 | 65.00 | 65.00 |

| Sundwiger                     |                     | SD01      | SD02      | SD03      | SD04       |
|-------------------------------|---------------------|-----------|-----------|-----------|------------|
| Tensile                       | soft                | 220 - 290 | 230 - 300 | 250 - 320 | 270 - 340  |
| strength in N/mm <sup>2</sup> | hard                | 300 - 400 | 360 - 460 | 400 - 500 | 510 - 610  |
| ·                             | springhard          | 400 - 500 | 460 - 560 | 500 - 600 | 610 - 710  |
|                               | super<br>springhard | 500 - 700 | 560 - 800 | 600 - 820 | 710 - 1000 |
| Elongation A100 in %,         |                     |           |           | 20        |            |

> 30

soft

#### About the Alloy

The strength of copper can be exceeded significantly by alloying of magnesium, thereby the conductivity is only slightly reduced.

By alloying of Mg in the range of 0.1 to 0.8 %, the ratio of tensile strength and conductivity can be adjusted very precisely. CuMg is suitable for electric connections, for connector pins and for overhead telephone lines.

In recent years, this alloy has become more and more important as a material for contact wire and catenary cables for high-speed trains.

This alloy family is used as a substitution for copper-cadmium which is already prohibited in many countries due to its toxic properties.

| Available Dimensions                 |  |              |  |
|--------------------------------------|--|--------------|--|
| Rolled, modi-<br>fied square<br>wire | 5.1 mm<br>7.4 mm   | max. 2000 kg |  |
| Round wire                           | 1.2 - 6.2 mm<br>in coils   | max. 100 kg  |  |
|                                      | 1.8 - 6.2 mm<br>on stands  | max. 1500 kg |  |
|                                      | 0.5 - 3 mm<br>on reels   | max. 1000 kg |  |
|                                      | 1.5 - 3 mm<br>on acropaks  | max. 400 kg  |  |
|                                      | on request:<br>in drums  | max. 400 kg  |  |
| Catenary wire                        | On drums, cross-section area:<br>100 / 120 / 150 mm <sup>2</sup><br>customized length<br>(max. 1.5 km) |              |  |
| Contact wire                         | On drums<br>(for high-speed trains)  |              |  |

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.

<sup>\*</sup> Reference values at room temperature

# Copper Magnesium SD01 | SD02 | SD03 | SD04 | SD05 |



| Correspondent Standards for Railway Applications: |  |  |  |
|---|--|--|--|
| DIN 17 666  | Low-alloyed wrought copper alloys  |  |  |
| EN 50 149   | Railway applications - stationary equipment, grooved contact wire of copper and copper alloys          |  |  |
| Ebs (DR-M) 25 - 45.020                            | Contact wire of copper-magnesium-wrought alloy, technical delivery conditions, overhead line Re 250 DR |  |  |
| DIN 43 138  | Flexible cables for catenary systems and return lines  |  |  |
| DIN 43 140  | Contact wire, technical delivery conditions  |  |  |
| DIN 48 200, Teil 2                                | Wire for catenary cables   |  |  |
| DIN 48 201, Teil 2                                | Catenary cables  |  |  |
| DIN 48 203, Teil 2                                | Wire and cables for wrought copper alloy lines   |  |  |
| DIN 48 300  | Wire for overhead telephone lines  |  |  |
| NF C 34 - 110 - 1                                 | Copper alloy wire for overhead line conductors   |  |  |
| NF C 34 - 110 - 2                                 | Copper alloy conductors for overhead lines   |  |  |
| NF C 34 - 110 - 3                                 | Hard drawn copper conductors for overhead lines  |  |  |
| SIP 1221  | Properties of bronze overhead lines  |  |  |

### **Your Contact Person**

Worldwide



Sundwiger Messingwerk GmbH

Hönnetalstraße 110 58675 Hemer Deutschland Tel. +49 2372 661-0

Fax +49 2372 661-259

 $\hbox{E-Mail: sales-sundwig@sundwiger-mw.com}\\$ 

www.sundwiger-mw.com

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.