

Copper KD00



Material Designation	
Sundwiger	KD00
DIN-EN Symbol	Cu-OF
DIN-EN	CW008A
UNS	C10200

About the Alloy
Cu-OF is a high-purity, oxygen-free, non-phosphorus-deoxidized copper. It has very high electrical and thermal conductivity, good weldability, and excellent soldering properties. It has excellent hot and cold forming properties and good corrosion resistance, especially in the atmosphere, due to the good adhesion of the oxide layer.

Reference to Standards	
DIN	EN 12166

Typical Applications
• Contacts • Fasteners • Screws and rivets for electrical applications

Physical Properties*		
Sundwiger	KD00	
Electrical conductivity	100	% IACS
Electrical conductivity	58	MS/m
Thermal coefficient of electrical resistance (0..100 °C)	3,81	10-3/K
Thermal conductivity	394	W/(m·K)
Thermal expansion coefficient (20..300 °C)	17,7	10-6/K
Density in g/cm ³	8,93	g/cm ³
Modulus of elasticity	130	GPa = kN/mm ²
* Reference values in soft condition		

Mechanical Properties*		
Sundwiger	KD00	
Tensile strength in N/mm ²	R220	220 - 260
	R240	240 - 300
	R290	290 - 360
	R360	≥ 360
Elongation A50 in % , soft		> 30
* Reference values		

Your Contact Person	
Worldwide	
Sundwiger Messingwerk GmbH Hönnetalstraße 110 58675 Hemer Deutschland Tel. +49 2372 661-0 Fax +49 2372 661-259 E-Mail: sales-sundwig@sundwiger-mw.com www.sundwiger-mw.com	

Available Dimensions		
Square wire	5,1 mm	max. 2000 kg
	7,4 mm	kg
Round-wire	1,2 - 6,2 mm in Coils	max. 200 kg
	1,8 - 6,2 mm on stands	max. 1000 kg
	0,5 - 3 mm on reels	max. 1000 kg
	1,5 - 3 mm on acropaks	max. 400 kg
	on request: in drums	max. 400 kg

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale. We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.